

Heat Shrink Tubes

3M™ GTI 3000 – Polyolefin



1. Product description

3M™ GTI 3000 is a range of flexible, thin walled RoHS Heat Shrink Tubes, made of crosslinked Halogen free Polyolefin. 3M™ GTI 3000 provides good insulation protection in various industrial applications. They are also suitable for cable marking and identification applications. 3M™ GTI 3000 tubes have a 3:1 shrink ratio and are available in the following colours: Clear, Black, Red, Yellow, Blue, White, Green, Grey and Green/Yellow striped.

2. Typical properties

2.1 Technical information

Physical properties	Value	Requirement	Test method
Colour	Clear, Black, Red, Yellow, Blue, White, Green, Grey, Green/Yellow striped	–	–
Shrink ratio	3:1	–	–
Tensile strength	25N/mm ²	>10	IEC 60684-2-19.1
Elongation at break	540%	>250	IEC 60684-2-19.2
Longitudinal change	-5-0%	-10<>+5	IEC 60684-2-9
Concentricity supplied (total wall)	80%	>65	IEC 60684-2-3
Concentricity fully recovered (outer wall)	90%	>85	IEC 60684-2-3
Secant modulus	80N/mm ²	50<>175	IEC 60684-2-19.4
Relative density	0.92g/cm ³	–	IEC 60684-2-4

Thermal tests			
Continuous operating temperature	-55<>135°C	–	–
Shrink temperature	135<>280°C	–	–
Heat shock	–	4 hrs at 200°C	IEC 60684-2-6
Tensile strength	25N/mm ²	>10	IEC 60684-2-19
Elongation at break	540%	>200	IEC 60684-2-19
Low temperature flexibility	Pass	4 hrs at -55°C No cracking after bending	IEC 60684-2-14
Copper corrosion	Pass	No corrosion	IEC 60684-2-33
Flammability	Not self-extinguishing	C (30s, 75mm)	IEC 60684-2-26

Electrical tests			
Volume resistivity	10 ¹⁴ Ωm	>10 ¹² at room temp.	IEC 60684-2-23
Breakdown voltage	34kV/mm	>21	IEC 60684-2-21

Chemical tests			
Selected fluids according to table 5 of IEC 60684-3-212 at 23°C, 24hrs	Pass N/mm ² / %	Tensile/elongation >7 / >200	IEC 60684-2-36

3. User information

3.1 Selection guide

Part number	Expanded ID min. (mm)	Recovered ID max. (mm)	Recovered wall thickness (nominal) (mm)
1.5	1.5	0.5	0.45
3.0	3.0	1.0	0.55
6.0	6.0	2.0	0.65
9.0	9.0	3.0	0.75
12.0	12.0	4.0	0.75
18.0	18.0	6.0	0.75
24.0	24.0	8.0	1.00
39.0	39.0	13.0	1.15

3.2 Agency approvals and self certifications

- ▶ Halogen free

3.3 Shelf life and storage

This product has a 5-year shelf life from date of manufacture when stored in a humidity controlled area (10°C to 27°C and <75% relative humidity).

4. Additional information

To request additional product information, see address below.

Important notice

All statements, technical information and recommendations contained in this document are based upon tests or experience that 3M believes are reliable. However, many factors beyond 3M's control can affect the use and performance of a 3M product in a particular application, including the conditions under which the product is used and the time and environmental conditions in which the product is expected to perform. Since these factors are uniquely within the user's knowledge and control, it is essential that the user evaluates the 3M product to determine whether it is fit for a particular purpose and suitable for the user's method or application.

Values presented have been determined by standard test methods and are average values not meant to be used for specification purposes.

All questions of warranty and liability relating to 3M products are governed by the terms of the respective sale subject, where applicable, to the prevailing law.

Electrical Markets Division

3M Deutschland GmbH
Carl-Schurz-Str.1
41453 Neuss
Germany

Reference: AABDD24306#EN 01
Issue date: 03.03.2020 – Supersedes new

Please recycle. © 3M 2021. 3M is a trademark of the 3M Company.
All rights reserved. OMG100100

