

ScotchcastTM

REACH 1907/2007/EC

Electrical Insulating Resin 1402FR

Product Description

3M[™] Scotchcast[™] Resin 1402FR is a halogen free, flame retardant, two component polyurethane resin for room temperature curing. The resin has been designed for flame retardant and chemical resistant property as well as electrical insulation and mechanical protection of electrical cables joints.

The 1402FR resin is classified as MIW (medium voltage insulation water curable) according Cenelec HD 631.1 S2 Standard.

Once the hardening is complete, the resin provides impact resistance and durability against moisture, hydro carbons and atmospheric corrosion.

Application

Electrical insulation and mechanical protection of low and medium voltage electrical joints installed for indoor and outdoor, underground and submerged applications in heavy conditions were flame retardancy or resistance against chemicals like hydro carbons is required.

Features

- Flame retardant
- Halogen Free
- Chemical resistant
- Good adhesion on metals and different plastics.
- Hydrophobic behaviour during the curing stage.
- Excellent hydrolytic stability
- Available with Closed Mix and Pour Delivery System
- Low exothermic reaction temperature.

Process Figures

Mixing Ratio (pbw)	A : B	100 : 20	
Pot Life	At 5 °C	35 min	
	At 23°C	20 min	
	At 40°C	8 min	

3M Deutschland GmbH Electrical Markets Division

Carl-Schurz-Straße 1 D-41453 Neuss Germany AABBCC78412 Issue 04

11.10.12

Typical Properties

Note: This data is not to be used for specifications. Values listed are typical and should not be considered minimum or maximum.

Property	Value	Specification
Part A Density Viscosity 23°C	1,60 g/cm³ 8100 mPas	ISO 3675 EN ISO 2555
Part B Density Viscosity 23°C	1,23 g/cm³ 140 mPas	ISO 3675 EN ISO 2555
Part A&B (mixed) Density Viscosity 23°C Exothermic Reaction Temp 40°C Hydrophobic Behaviour Volume Shrinkage	1,57 g/cm³ 3.500 mPas 65 °C Passed 3,0 %	ISO 3675 EN ISO 2555 HD 631.1 S2 HD 631.1 S2 EN ISO 3521
Part A&B (cured*)		
Mechanical properties Hardness Shore D Tensile Strength Elongation at Break Impact Strength (without notch)	75 25 MPa 2 % >5 KJ/m²	EN ISO 868 EN ISO 527 EN ISO 527 EN ISO 179
Electrical properties Volume resistivity at 23 °C at 80 °C Dielectric Strength at 23 °C	8,0E+14 Ωcm 2,5E+11 Ωcm >30 kV/mm	IEC 60250 EN 60243-1
Dissipation factor at 23 °C	<0,04 <0,13	IEC 60250
at 80 °C Dielectric constant at 23 °C at 80 °C	<0,13 <6 <8	IEC 60250

3M Deutschland GmbH Electrical Markets Division Carl-Schurz-Straße 1 D-41453 Neuss Germany

AABBCC78412 Issue 04

11.10.12

Elect. prop. after dry ageing Volume resistivity at 23 °C Dielectric Strength at 23 °C Dielectric constant at 23 °C Property	> 1,0E+14 Ωcm > 30 kV/mm <6 Value	IEC 60250 EN 60243-1 IEC 60250 Specification
Elect. prop. after wet ageing Volume resistivity at 23 °C Dielectric Strength at 23 °C Dielectric constant at 23 °C	> 1,0E+14 Ωcm > 30 kV/mm <6	IEC 60250 EN 60243-1 IEC 60250
Flame retardant properties Flammability Content of halogen Conductivity of smoke gas Acidity of smoke gas	V0 (3mm) <0,5 % <10 μS/mm >4,3	UL94 EN 5067-2-1 EN 5067-2-2 EN 5067-2-2
Chemical resistance Unleaded petrol (Super 95) Diesel fuel Insulating Oil Hydraulic Oil Salt solution 10% *curing and aging cycles according to C	<4,0 % <0,05 % <0,10 % <0,10 % <0,30 % tenelec HD631.1 S2	EN 60455-2 EN 60455-2 EN 60455-2 EN 60455-2 EN 60455-2

User Information:

The resin will be supplied, in two-chamber plastic pouches with peelable barrier in the correct stoichiometric proportion. This type of packaging will assure the correct mixing ratio for applying the resin.

The packaging includes a Closed Mix and Pour Delivery System. The integrated pouring spout will be opened while attaching the mixed resin bag to the housing of the joint or by using the supplied opener.

For other information, relevant for the usage of the resin, like Gel-Time, Pot-Life, viscosity, density etc. please see above the typical properties.

Storage:

3M™ Scotchcast™ Resin 1402FR has a shelf life of at least 36 months when stored between 10°C and 40°C with a humidity level < 75 % in the originally sealed bag. The expiration date of each product appears on the product label. Storage beyond the date specified on the label does not necessarily mean that the product is no longer usable. In this case however, it is the responsibility of the user to determine applicability of the resin.

Safety and Handling:

3M provides its customers with a product specific Material Safety Data Sheet (MSDS) to cover potential health effects, safe handling, storage, use and disposal information. 3M strongly encourages its customers to review the MSDS on its products prior to their use.

Product Stewardship:

3M has a fundamental concern for all who make, distribute and use its products, and for the environment in which we live. This concern is the basis of our philosophy and policies by which we assess the health and environmental information on our products and then take the appropriate steps to protect employee, the public health and the environment.

Customer Notice:

3M encourages its customers and potential users of 3M products to review their applications for such products from the standpoint of human health and environmental quality. To help ensure that 3M products are not used in ways for which they were not intended or tested. 3M personnel are available to assist customers in dealing with ecological and product safety considerations. Your 3M sales representative can arrange for the proper contacts.

Regulatory Status:

3M[™] Scotchcast[™] Resin 1402FR is in compliance with all European directives and regulations, relevant for this product.

The 1402FR Resin is in compliance with EU regulation 1907/2007/EC (REACH).

3M and Scotchcast are trademarks of 3M Company.

Important Notice

All statements, technical information and recommendations related to the Seller's products are based on information believed to be reliable, but the accuracy or completeness thereof is not guaranteed. Before utilizing the product, the user should determine the suitability of the product for its intended use. The user assumes all risks and liability whatsoever in connection with such use.

Any statements or recommendations of the Seller which are not contained in the Seller's current publications shall have no force or effect unless contained in an agreement signed by an authorized office of the Seller.

The statements contained herein are made in lieu of all warranties, expressed or implied, including but not limited to the implied warranties of merchantability and fitness for a particular purpose which warranties are hereby expressly disclaimed.

SELLER SHALL NOT BE LIABLE TO THE USER OR ANY OTHER PERSON UNDER ANY LEGAL THEORY; INCLUDING BUT NOT LIMITED TO NEGLIGENCE OR STRICT LIABILITY; FOR ANY INJURY OR FOR ANY DIRECT; INCIDENTAL OR CONSEQUENTIAL DAMAGES SUSTAINED OR INCURRED BY REASON OF THE USE OF ANY OF THE SELLER'S PRODUCTS.