

Guaina trecciata espansibile
Expansible braided sleeve




Materiale Poliestere PET - Material Polyester PET

Articolo colore nero Item black colour	Misura Size Ø mm	Espansibilità Expansibility	
		Min mm	Max mm
GNB05PE	5	3,2	11,1
GNB08PE	8	6,4	12,7
GNB10PE	10	4,8	15,9
GNB12PE	12	6,4	19,1
GNB15PE	15	9,5	25,4
GNB20PE	20	12,7	31,8
GNB25PE	25	15,9	38,1
GNB30PE	30	19,1	44,5
GNB40PE	40	25,4	63,5
GNB50PE	50	38,1	88,9



Materiale Poliestere PET - Material Polyester PET

Articolo colore grigio Item grey colour	Misura Size Ø mm	Espansibilità Expansibility	
		Min mm	Max mm
GGB05PE	5	3,2	11,1
GGB08PE	8	6,4	12,7
GGB10PE	10	4,8	15,9
GGB12PE	12	6,4	19,1
GGB15PE	15	9,5	25,4
GGB20PE	20	12,7	31,8
GGB25PE	25	15,9	38,1
GGB30PE	30	19,1	44,5
GGB40PE	40	25,4	63,5
GGB50PE	50	38,1	88,9



Materiale Nylon PA 6.6 - Material Nylon PA 6.6

Articolo colore nero Item black colour	Misura Size Ø mm	Espansibilità Expansibility	
		Min mm	Max mm
GNB05PA	5	3,2	11,1
GNB08PA	8	6,4	12,7
GNB10PA	10	4,8	15,9
GNB12PA	12	6,4	19,1
GNB15PA	15	9,5	25,4
GNB20PA	20	12,7	31,8
GNB25PA	25	15,9	38,1
GNB30PA	30	19,1	44,5
GNB40PA	40	25,4	63,5
GNB50PA	50	38,1	88,9



Caratteristiche tecniche - Technical features

Materiale - Material	PET	PA 6.6
Diametro monofilamento - Monofilament diameter	0,25 mm	0,25 mm
Temperature di utilizzo - Temperature range	-50°C +150°C	-45°C +150°C
Autoestinguenza - Self-extinguishing	UL94-V2	UL94-V2
Temperatura di fusione - Melting temperature	+250°C	+260°C
Resistenza UV - UV resistance		Buona - Good
Resistenza chimica - Chemical resistance	Buona - Good	Buona - Good