



#### **DICHIARAZIONE DI PRESTAZIONE**

per il Sistema a iniezione fischer FIS V (ancorante chimico per i collegamenti di barre di armatura post-installate)

ΙT

1. Codice di identificazione unico del prodotto-tipo:

DoP 0229

2. Usi previsti:

5. Sistemi di VVCP:

Sistema per il collegamento di barre di armatura post-installate con resina per l'utilizzo in Vedi appendice, in particolare gli allegati da B1- B11 fischerwerke GmbH & Co. KG, Otto-Hahn-Straße 15, 79211 Denzlingen, Germany

3. Fabbricante:

4. Mandatario:

6. Documento per la valutazione europea: EAD 330087-00-0601 Valutazione tecnica europea: ETA-08/0266; 2020-06-15

Organismo di valutazione tecnica: DIBt- Deutsches Institut für Bautechnik Organismi notificati: 1343 MPA Darmstadt / 2873 TU Darmstadt

1

7. Prestazioni dichiarate:

Resistenza meccanica e stabilità (BWR 1)

Resistenza caratteristica al carico di tensione (carico statico e quasi-statico):

Resistenza di aderenza per armature post-inserite:

Allegati C1 Fattore di riduzione: Allegati C1

Fattore di amplificazione per la lunghezza di

ancoraggio minima:

Allegati C1

Sicurezza in caso di incendio (BWR 2)

Reazione al fuoco:

Resistenza al fuoco: Allegati C2, C3 Resistenza di aderenza per temperatura

Fischer DATA DOP\_ECs\_V25.xlsm 1/2





8. <u>Documentazione tecnica appropriata e/o documentazione tecnica specifica:</u>

La prestazione del prodotto sopra identificato è conforme all'insieme delle prestazioni dichiarate. La presente dichiarazione di prestazione è emessa, in conformità al regolamento (UE) n. 305/2011, sotto la sola responsabilità del fabbricante sopra identificato.

Firmato a nome e per conto del fabbricante da:

Thilo Pregartner, Dr.-Ing.
Tumlingen, 2020-06-29

ppa. The Mx

Peter Schillinger, Dipl.-Ing.

i.V. P. St

Questa Dichiarazione di Prestazione (DoP) è stata preparata in varie lingue. In caso di contestazioni sull'interpretazione, prevarrà sempre la versione inglese.

L'Appendice include informazioni volontarie e complementari in lingua inglese che superano i requisiti di legge (lingua specificata in modo neutrale).

Fischer DATA DOP\_ECs\_V25.xlsm 2/ 2

#### **Specific Part**

#### 1 Technical description of the product

The subject of this European technical assessment is the post-installed connection, by anchoring or overlap connection joint, of reinforcing bars (rebars) in existing structures made of normal weight concrete, using the injection mortar FIS V in accordance with the regulations for reinforced concrete construction.

Reinforcing bars with a diameter  $\phi$  from 8 to 28 mm or the fischer rebar anchor FRA of sizes M12 to M24 according to Annex A and the fischer injection mortar FIS V are used for the post-installed rebar connection. The steel element is placed into a drilled hole filled with injection mortar and is anchored via the bond between embedded reinforcing bar, injection mortar and concrete.

The product description is given in Annex A.

# 2 Specification of the intended use in accordance with the applicable European assessment Document

The performances given in Section 3 are only valid if the anchor is used in compliance with the specifications and conditions given in Annex B.

The verifications and assessment methods on which this European Technical Assessment is based lead to the assumption of a working life of the rebar connections of at least 50 years. The indications given on the working life cannot be interpreted as a guarantee given by the producer, but are to be regarded only as a means for choosing the right products in relation to the expected economically reasonable working life of the works.

#### 3 Performance of the product and references to the methods used for its assessment

#### 3.1 Mechanical resistance and stability (BWR 1)

Essential characteristic	Performance
Characteristic resistance under static and quasi-static loading	See Annex C 1

#### 3.2 Safety in case of fire (BWR 2)

Essential characteristic	Performance
Reaction to fire	Class A1
Resistance to fire	See Annex C 2 and C 3

# 4 Assessment and verification of constancy of performance (AVCP) system applied, with reference to its legal base


In accordance with European Assessment Document EAD No. 330087-00-0601, the applicable European legal act is: [96/582/EC].

The system to be applied is: 1

# Installation conditions and application examples reinforcing bars, part 1


#### Figure A1.1:

Overlap joint with existing reinforcement for rebar connections of slabs and beams




## Figure A1.2:

Overlap joint with existing reinforcement at a foundation of a column or wall where the rebars are stressed



#### Figure A1.3:

End anchoring of slabs or beams (e.g. designed as simply supported)



Figures not to scale

Rebar connection	with	fischer	injection	mortar	FIS	٧
------------------	------	---------	-----------	--------	-----	---

# **Product description**

Installation conditions and application examples reinforcing bars, part 1


## Annex A 1

Appendix 2/21

# Installation conditions and application examples reinforcing bars, part 2


#### Figure A2.1:

Rebar connection for stressed primarily in compression



#### Figure A2.2:

Anchoring of reinforcement to cover the enveloped line of acting tensile force in the bending member




Note to figure A1.1 to A1.3 and figure A2.1 to A2.2

In the figures no traverse reinforcement is plotted, the transverse reinforcement shall comply with EN 1992-1-1: 2004+AC:2010.

Preparing of joints according to Annex B 2

Figures not to scale


Rebar connection with fischer injection mortar FIS V	
Product description	Annex A 2
Installation conditions and application examples reinforcing bars, part 2	Appendix 3/ 21



Rebar connection with fischer injection mortar FIS V

Product description
Installation conditions and application examples fischer rebar anchors FRA, part 3

Appendix 4/ 21



# Properties of reinforcing bars (rebar)

#### Figure A5.1:



- The minimum value of related rip area f<sub>R,min</sub> according to EN 1992-1-1:2004+AC:2010
- The maximum outer rebar diameter over the rips shall be:
  - The nominal diameter of the rip  $\phi$  + 2 \* h (h ≤ 0,07 \*  $\phi$ )
  - ο (φ: Nominal diameter of the bar; h: rip height of the bar)

#### Table A5.1: Installation conditions for rebars

Nominal diameter of the bar		ф	8 <sup>1)</sup>	10 <sup>1)</sup>	12 <sup>1)</sup>	14	16	20	25	28
Nominal drill hole diameter	d <sub>0</sub>		10 12	12 14	14 16	18	20	25	30	35
Drill hole depth	$h_0$		$h_0 = I_v$							
Effective embedment depth	Ιν	[mm]	acc. to static calculation							
Minimum thickness of concrete member	h <sub>min</sub>			, + 30 ≥ 100)			l <sub>v</sub>	+ 2d <sub>0</sub>		

<sup>1)</sup> Both drill hole diameters can be used

### Table A5.2: Materials of rebars

Designation	Reinforcing bar (rebar)
Reinforcing bar  FN 1992-1-1:2004+AC:2010 Annex C	Bars and de-coiled rods class B or C with $f_{yk}$ and k according to NDP or NCL of EN 1992-1-1/NA:2013 $f_{uk} = f_{tk} = k \cdot f_{yk}$

Figures not to scale

Rebar connection with fischer injection mortar FIS V

Product description
Properties and materials of reinforcing bars (rebar)

Annex A 5

Appendix 6/ 21

# Figure A6.1: 1 2 3 4 head marking

Head marking e.g.: FRA (for stainless steel)

FRA C (for high corrosion-resistant steel)

Table A6.1: Installation conditions for fischer rebar anchors FRA

Threaded diameter			М1	2	M16	M20	M24
Nominal diameter	ф	[mm]	12	2	16	20	25
Width across flat	SW	[mm]	19	)	24	30	36
Nominal drill bit diameter	d <sub>0</sub>	[mm]	14 <sup>2)</sup>	16	20	25	30
Drill hole depth ( $h_0 = l_{e,ges}$ )	l <sub>e,ges</sub>	[mm]			l <sub>v</sub> +	- le	
Effective embedment depth	l <sub>v</sub>	[mm]	acc. to static calculation				
Distance concrete surface to welded join	l <sub>e</sub>	[mm]	100				
Diameter of clearance	Pre-positioned ≤ d <sub>f</sub>	[mm]	14	ļ	18	22	26
hole in the fixture <sup>1)</sup>	Push through ≤ d <sub>f</sub>	[mm]	18	}	22	26	32
Minimum thickness of concrete member	h <sub>min</sub>	[mm]	h <sub>0+</sub> ; (≥ 10			h <sub>0</sub> + 2d <sub>0</sub>	
Maximum torque moment fo attachment of the fixture	r max T <sub>fix</sub>	[Nm]	50	)	100	150	150

<sup>1)</sup> For bigger clearance holes in the fixture see EN 1992-4

Table A6.2: Materials of fischer rebar anchors FRA

Part	Description	Materials						
		FRA	FRA C					
1	Reinforcing bar	B500B acc. to	DIN 488-1:2009					
2	Round bar with partial or full thread	Stainless steel acc. to EN 10088-1:2014	High corrosion-resistant steel acc. to EN 10088-1:2014					
3	Washer	Stainless steel acc. to EN 10088-1:2014	High corrosion-resistant steel acc. to EN 10088-1:2014					
4 Hexagon nut		Stainless steel acc. to EN 10088-1:2014, strength class 80; acc. to EN ISO 3506:2009	High corrosion-resistant steel acc. to EN 10088-1:2014, strength class 80; acc. to EN ISO 3506:2009					

Figures not to scale

Rebar connection with fischer injection mortar FIS V

**Product description** 

Properties and materials of fischer rebar anchors FRA

Annex A 6

Appendix 7/21

<sup>2)</sup> Both drill bit diameters can be used

# Specifications of intended use (part 1)

# **Table B1.1:** Overview use and performance categories

Anchorages subject	t to	FIS V with				
			cing bar	fischer rebar anchor FRA		
Hammer drilling with standard drill bit	***********		all s	izes		
Hammer drilling with hollow drill bit (fischer "FHD", Heller "Duster Expert"; Bosch "Speed Clean"; Hilti "TE-CD, TE- YD")	Ī	Nominal drill bit diameter (d₀) 12 mm to 35 mm				
Static and quasi static load, in	uncracked concrete cracked concrete	all sizes	Tables: C1.1 C1.2 C1.3	all sizes	Tables: C1.1 C1.2 C1.3	
Installation temperature		$T_{i,min} = 0$ °C to $T_{i,max} = +40$ °C				
Fire exposure		all sizes	Annex C2	no performa	ince assessed	

Rebar connection with	fischer injection m	nortar FIS V
-----------------------	---------------------	--------------

Specifications (part 1)

# Specifications of intended use

#### Anchorages subject to:

- Static and guasi-static loads: reinforcing bar (rebar) size 8 mm to 28 mm
- Fire exposure

#### Base materials:

- Compacted reinforced or unreinforced normal weight concrete without fibres according to EN 206:2013+A1:2016
- Strength classes C12/15 to C50/60 according to EN 206:2013+A1:2016
- Maximum chloride content of 0,40 % (CL 0.40) related to the cement content according to EN 206:2013+A1:2016
- · Non-carbonated concrete

Note: In case of a carbonated surface of the existing concrete structure the carbonated layer shall be removed in the area of the post-installed rebar connection with a diameter of  $\phi$  + 60 mm prior to the installation of the new rebar. The depth of concrete to be removed shall correspond to at least the minimum concrete cover in accordance with EN 1992-1-1:2004+AC:2010. The foregoing may be neglected if building components are new and not carbonated and if building components are in dry conditions.

#### Temperature Range:

- 40°C to +80°C (max. short term temperature +80°C and max long term temperature +50°C).

#### Installation temperature:

0 °C to +40 °C

#### Use conditions (Environmental conditions) for fischer rebar anchors FRA

- Structures subject to dry internal conditions (fischer rebar anchors FRA and FRA C)
- Structures subject to external atmospheric exposure (including industrial and marine environment) and to permanently damp internal condition, if no particular aggressive conditions exist (fischer rebar anchors FRA and FRA C)
- Structures subject to external atmospheric exposure and to permanently damp internal condition, if other particular aggressive conditions exist (fischer rebar anchors FRA C)

  Note: Particular aggressive conditions are e.g. permanent, alternating immersion in seawater or the splash zone of seawater, chloride atmosphere of indoor swimming pools or atmosphere with extreme chemical pollution (e.g. in

#### Design:

- Anchorages are designed under the responsibility of an engineer experienced in anchorages and concrete work.
- Verifiable calculation notes and drawings are prepared taking account of the forces to be transmitted.
- Design according to EN 1992-1-1:2004+AC:2010 and Annex B 3 and B 4.

desulphurization plants or road tunnels where de-icing materials are used).

• The actual position of the reinforcement in the existing structure shall be determined on the basis of the construction documentation and taken into account when designing.

#### Installation:


- Dry or wet concrete
- Water filled holes, only with 380 ml, 400 ml or 410 ml cartridges
- Hole drilling by hammer drill, hollow drill or compressed air drill mode
- Overhead installation allowed
- The installation of post-installed rebar respectively fischer rebar anchor FRA shall be done only by suitable trained installer and under Supervision on site; the conditions under which an installer may be considered as suitable trained and the conditions for Supervision on site are up to the Member States in which the installation is done.
- Check the position of the existing rebars (if the position of existing rebars is not known, it shall be determined using a rebar detector suitable for this purpose as well as on the basis of the construction documentation and then marked on the building component for the overlap joint).

Rebar connection with fischer injection mortar FIS V	
Intended use	Annex B 2
Specifications (part 2)	Appendix 9/ 21

# General construction rules for post-installed rebars

#### Figure B3.1:

- · Only tension forces in the axis of the rebar may be transmitted.
- The transfer of shear forces between new concrete and existing structure shall be designed additionally according to EN 1992-1-1:2004+AC:2010.
- The joints for concreting must be roughened to at least such an extent that aggregate protrude.



- $^{1)}$  If the clear distance between lapped bars exceeds 4  $\varphi$  then the lap length shall be increased by the difference between the clear bar distance and 4  $\varphi$ 
  - c concrete cover of post-installed rebar
  - c<sub>1</sub> concrete cover at end-face of existing rebar
  - c<sub>min</sub> minimum concrete cover according to table B5.1 and to EN 1992-1-1:2004+AC:2010, Section 4.4.1.2
  - φ nominal diameter of reinforcing bar
  - l<sub>0</sub> lap length, according to EN 1992-1-1:2004+AC:2010
  - $I_v$  effective embedment depth,  $\geq I_0 + c_1$
  - d<sub>0</sub> nominal drill bit diameter, see Annex B 6

Figures not to scale


Rebar connection with fischer injection mortar FIS V	
Intended use General construction rules for post-installed rebars	Annex B 3

Appendix 10/21

# General construction rules for post-installed rebar anchors FRA

#### Figure B4.1:

- · Only tension forces in the axis of the FRA may be transmitted.
- The tension force must be transferred via an overlap joint to the reinforcement in the building part.
- The transmission of the shear load shall be ensured by appropriate additional measures, e.g. by shear lugs or by anchors with a European Technical Assessment (ETA).
- In the anchor plate, the holes for the tension anchor shall be executed as slotted holes with the axis in the direction of the shear force.



 $^{1)}$  If the clear distance between lapped bars exceeds 4  $\phi$  then the lap length shall be increased by the difference between the clear bar distance and 4  $\phi$ .

c concrete cover of post-installed rebar anchor FRA

c<sub>1</sub> concrete cover at end-face of existing rebar

c<sub>min</sub> minimum concrete cover according to table B5.1 and to EN 1992-1-1:2004+AC:2010, Section 4.4.1.2

φ nominal diameter of reinforcing bar

lo lap length, according to EN 1992-1-1:2004+AC:2010, Section 8.7.3

 $I_{e,ges}$  overall embedment depth,  $\geq I_0 + I_e$ d<sub>0</sub> nominal drill bit diameter, see Annex B 6

le length of the bonded in threaded part

t<sub>fix</sub> thickness of the fixture l<sub>v</sub> effective embedment depth

Figures not to scale

	rigures not to scale
Rebar connection with fischer injection mortar FIS V	
Intended use	Annex B 4
General construction rules for post-installed rebar anchors FRA	Appendix 11/ 21

**Table B5.1:** Minimum concrete cover c<sub>min</sub><sup>1)</sup> depending of the drilling method and the drilling tolerance

	nominal diameter	Minimum concrete cover c <sub>min</sub>				
Drilling method	of reinforcing bar φ [mm]	Without drilling aid [mm] With drilli		ling aid [mm]		
Hammer drilling with standard drill	< 25	30 mm + 0,06 l <sub>v</sub> ≥ 2 ф	30 mm + 0,02 l <sub>v</sub> ≥ 2 ф			
bit	≥ 25	40 mm + 0,06 l <sub>ν</sub> ≥ 2 φ	40 mm + 0,02 l <sub>ν</sub> ≥ 2 φ			
Hammer drilling with hollow drill bit (fischer "FHD", Heller "Duster	< 25	30 mm + 0,06 l <sub>v</sub> ≥ 2 ф	30 mm + 0,02 l <sub>ν</sub> ≥ 2 φ	Drilling aid		
Expert"; Bosch "Speed Clean"; Hilti "TE-CD, TE- YD")	≥ 25	40 mm + 0,06 l <sub>ν</sub> ≥ 2 φ	40 mm + 0,02 l <sub>ν</sub> ≥ 2 φ			
Compressed air	< 25	50 mm + 0,08 l <sub>v</sub>	50 mm + 0,02 l <sub>v</sub>			
drilling	≥ 25	60 mm + 0,08 l <sub>v</sub> ≥ 2 ф	60 mm + 0,02 l <sub>v</sub> ≥ 2 ф			

<sup>&</sup>lt;sup>1)</sup> See Annex B3, figure B3.1 and Annex B4, figure B4.1 Note: The minimum concrete cover as specified in EN 1992-1-1:2004+AC:2010 must be observed.

**Table B5.2:** Dispensers and cartride sizes corresponding to maximum embedment depth  $I_{v,max}$ 

reinforcing bars (rebar)	rebar anchor	Manual dispenser	Accu and pneumatic dispenser (small)	Pneumatic dispenser (large)
baro (robar)	FRA		Cartridge size	(10.90)
		< 50	0 ml	> 500 ml
φ [mm]	thread [M]	l <sub>v,max</sub> / l <sub>e,ge</sub>	es,max [mm]	l <sub>v,max</sub> / l <sub>e,ges,max</sub> [mm]
8			1000	
10			1000	
12	FRA 12	1000	1200	1800
14			1200	1800
16	FRA 16		1500	
20	FRA 20	700	1300	
25	FRA 24	700	1000	2000
28		500	700	2000

Rebar connection with fischer injection mortar FIS V	
Intended use	Annex B 5
Minimum concrete cover; dispenser and cartridge sizes corresponding to maximum embedment depth	Appendix 12/ 21

Table Bo.1: Working times twork and curing times toure								
Temperature in the anchorage base		vorking time <sup>1)</sup>	Minimum curing time <sup>2)</sup> t <sub>cure</sub>					
[℃]	FIS V	FIS VS Low Speed	FIS V	FIS VS Low Speed				
>±0 to +5	13 min <sup>3)</sup>		3 h	6 h				
>+5 to +10	9 min <sup>3)</sup>	20 min	90 min	3 h				
>+10 to +20	5 min	10 min	60 min	2 h				
>+20 to +30	4 min	6 min	45 min	60 min				
>+30 to +40	2 min <sup>4)</sup>	4 min	35 min	30 min				

<sup>1)</sup> Maximum time from the beginning of the injection to rebar / FRA setting and positioning

**Table B6.2:** Installation tools for drilling and cleaning the bore hole and injection of the mortar

reinforcing	inforcing rebar Drilling and cleaning						Injection		
bars (rebar)	anchor FRA	Nominal drill bit diameter	Diameter of cutting edge	Steel brush diameter	Diameter of cleaning nozzle	Diameter of extension tube	Injection adapter		
φ [mm]	thread [M]	d₀ [mm]	d <sub>cut</sub> [mm]	d₀ [mm]	[mm]	[mm]	[colour]		
81)		10	≤ 10,50	11,0					
8'7		12	≤ 12,50	12,5			nature		
101)		12	≤ 12,50	12,5	11	9 —	Hature		
10 /		14	≤ 14,50	15		]	blue		
121)	12¹) FRA 12¹)	14	≤ 14,50	15			blue		
12"		16	≤ 16,50	17	15		red		
14		18	≤ 18,50	19			yellow		
16 FRA 16		20	≤ 20,55	21,5	10		green		
20	FRA 20	25	≤ 25,55	26,5	19	9 or 15	black		
25	FRA 24	30	≤ 30,55	32	28		grey		
28		35	≤ 35,70	37			brown		

<sup>1)</sup> Both drill bit diameters can be used

#### Intended use

Working times and curing times;

Installation tools for drilling and cleaning the bore hole and injection of the mortar

#### Annex B 6

Appendix 13/21

<sup>2)</sup> For wet concrete the curing time must be doubled

 $<sup>^{3)}</sup>$  If the temperature in the concrete falls below  $10\,^{\circ}\mathrm{C}$  the cartridge has to be warmed up to +15  $^{\circ}\mathrm{C}$ .

<sup>&</sup>lt;sup>4)</sup> If the temperature in the concrete exceeds 30 °C the cartridge has to be cooled down to +15 °C up to 20 °C

## Safety regulations



Review the Safety Data Sheet (SDS) before use for proper and safe handling! Wear well-fitting protective goggles and protective gloves when working with mortar FIS V / FIS VS Low Speed.

Minimum concrete cover c<sub>min</sub> see table B5.1

Important: Observe the instructions for use provided with each cartridge.

## Installation instruction part 1; Installation with FIS V / FIS VS Low Speed

## Hole drilling

Note: Before drilling, remove carbonized concrete; clean contact areas (see Annex B 2) In case of aborted drill holes the drill hole shall be filled with mortar.

# Hammer drilling or compressed air drilling Drill the hole to the required embedment depth using a 1a hammer drill with carbide drill bit set in rotation hammer mode or a pneumatic drill. Drill bit sizes see table B6.2. Hammer drilling with hollow drill bit Drill the hole to the required embedment depth using a hammer drill with hollow drill bit in rotation hammer mode. 1b Dust extraction conditions see drill hole cleaning annex B8. Drill bit sizes see table B6.2. $\mathbf{C}_{\text{drill}}$ Measure and control concrete cover c $(C_{drill} = C + \emptyset / 2)$ Drill parallel to surface edge and to existing rebar. Where applicable use fischer drilling aid. $I_v$ , $I_{e,ges}$ 2 For holes $l_v > 20$ cm use drilling aid. Three different options can be considered: A) fischer drilling aid B) Slat or spirit level C) Visual check

Rebar connection with	fischer injection	mortar FIS V
-----------------------	-------------------	--------------

#### Intended use

Safety regulations; Installation instruction part 1, hole drilling

Annex B 7

Appendix 14/21

Installation instruction part 2; Installation with FIS V / FIS VS Low Speed								
Drill hole cleaning								
	Hammer or compressed air drilling							
	3x	Blowing three times from the back of the hole with the appropriate nozzle (oil-free compressed air ≥ 6 bar) until return air strear is free of noticeable dust. Personal protective equipment must be used (see regulation Annex B7).						
<b>3</b> a	3x	Brushing (with power drill) three times with the suitable brush size (hole diameter). Switch on the power drill steel brush into the drill hole. The brush in noticeable resistance when it is inserted this is not the case, use a new or larger to the thin the processory, check with brush inspection Suitable brushes see table B6.2.	after inserting the must produce a into the drill hole. If brush.					
	3x	Blowing three times from the back of the hole with nozzle (oil-free compressed air ≥ 6 bar) u is free of noticeable dust. Personal protective equipment must be u Annex B7).	ıntil return air stream					
	Hammer drilling with hollow drill bit							
3b		Use a suitable dust extraction system, e. fischer FVC 35 M or a comparable dust e equivalent performance data.  Drill the hole with hollow drill bit. The dust has to extract the drill dust nonstop durin and must be adjusted to maximum powe No further drill hole cleaning necessary	extraction system with t extraction system g the drilling process					
No further drill hole cleaning necessary								
Reba	ar connection with fischer injection n	nortar FIS V						
Intended use Installation instruction part 2, drill hole cleaning  Appendix 15/								

# Installation instruction part 3; Installation with FIS V / FIS VS Low Speed reinforcing bars (rebar) / fischer rebar anchor FRA and cartridge preparation Before use, make asure that the rebar or the rebar anchor FRA is dry and free of oil or other residue. 4 Mark the embedment depth l<sub>v</sub> (e.g. with tape) Insert rebar in borehole, to verify drill hole depth and setting depth l<sub>v</sub> resp. l<sub>e,ges</sub> Twist off the sealing cap Twist on the static mixer (the spiral in the static mixer must be 5 clearly visible). Place the cartridge into a suitable dispenser. 6 Press out approximately 10 cm of mortar until the resin is 7 permanently grey in colour. Mortar which is not grey in colour will not cure and must be disposed.

Rebar connection with fischer injection mortar FIS V	/
--	---

#### Intended use

Installation instruction part 3, reinforcing bars (rebar) / fischer rebar anchor FRA and cartridge preparation


Annex B 9

Appendix 16/21

# Installation instruction part 4; Installation with FIS V / FIS VS Low Speed

Injection of the mortar; borehole depth ≤ 250 mm

8a




Inject the mortar from the back of the hole towards the front and slowly withdraw the mixing nozzle step by step with each trigger pull. Avoid bubbles.

Fill holes approximately 2/3 full, to ensure that the annular gap between the rebar and the concrete will be completely filled with adhesive over the entire embedment length.


After injecting, release the dispenser. This will prevent further mortar discharge from the mixing nozzle.

# Injection of the mortar; borehole depth > 250 mm



Assemble mixing nozzle FIS MR Plus or FIS UMR, extension tube and appropriate injection adapter (see table B6.2)

Mortar level mark



Mark the required mortar level  $l_m$  and embedment depth  $l_\nu$  resp.  $l_{\text{e,ges}}$  with tape or marker on the injection extension tube.


a) Estimation:

$$l_m = \frac{1}{3} * l_v resp. l_m = \frac{1}{3} * l_{e,ges}$$

b) Precise equation for optimum mortar volume:

$$l_m = l_v \, resp. \, l_{e,ges} \, \left( (1,2 * \frac{d_s^2}{d_0^2} - 0,2) \right)$$
[mm]

8b




Insert injection adapter to back of the hole. Begin injection allowing the pressure of the injected adhesive mortar to push the injection adapter towards the front of the hole. Do not actively pull out!

Fill holes approximately 2/3 full, to ensure that the annular gap between the rebar and the concrete will be completely filled with adhesive over the embedment length.

When using an injection adapter continue injection until the mortar level mark  $l_m$  becomes visible.

Maximum embedment depth see table B5.2



After injecting, release the dispenser. This will prevent further mortar discharge from the mixing nozzle.

# Rebar connection with fischer injection mortar FIS V

#### Intended use

Installation instruction part 4, mortar injection

Annex B 10

Appendix 17/21

# Installation instruction part 5; Installation with FIS V / FIS VS Low Speed Insert rebar / rebar anchor FRA Insert the rebar / rebar anchor FRA slowly twisted into the borehole until the 9 embedment mark is reached. For overhead installation, support the rebar / rebar anchor FRA and secure it 10 from falling till mortar started to harden, e.g. using wedges. After installing the rebar or FRA the annular gap must be completely filled with mortar. Proper installation 11 Desired embedment depth is reached lv: embedment mark at concrete surface Excess mortar flows out of the borehole after the rebar has been fully inserted up to the embedment mark. Observe the working time "twork" (see table B 6.1), which varies according to temperature of base material. Minor adjustments to the rebar / rebar anchor FRA position may be performed during the working time 12 Full load may be applied only after the curing time "tcure" has elapsed (see table B 6.1) Mounting the fixture, 13 max Tfix see table A 6.1 Rebar connection with fischer injection mortar FIS V Annex B 11 Intended use

Installation instruction part 5, insert rebar / rebar anchor FRA

Appendix 18/21

# Minimum anchorage length and minimum lap length

The minimum anchorage length  $l_{b,min}$  and the minimum lap length  $l_{o,min}$  according to EN 1992-1-1 shall be multiply by the relevant amplification factor  $\alpha_{lb}$  according to table C1.1.

**Table C1.1:** Amplification factor α<sub>lb</sub> related to concrete strength class and drilling method

Concrete strength class	Drilling method	Amplification factor $\alpha_{lb}$	
	Hammer drilling with standard drill bit	1,0	
C12/15 to C50/60	Hammer drilling with hollow drill bit (fischer "FHD", Heller "Duster Expert"; Bosch "Speed Clean"; Hilti "TE-CD, TE-YD")	1,0	
	Compressed air drilling	1,0	

**Table C1.2:** Bond efficiency factor k<sub>b</sub> for hammer drilling, hollow drilling and compressed air drilling

Hammer drilling, hollow drilling and compressed air drilling

Rebar / rebar	r Bond efficiency factor k <sub>b</sub>								
anchor FRA				Concre	ete strengtl	n class			
φ [mm]	C12/15	C16/20	C20/25	C25/30	C30/37	C35/45	C40/50	C45/55	C50/60
8 to 28					1,00				

**Table C1.3:** Design values of the bond strength f<sub>bd,PIR</sub> in N/mm² for hammer drilling, hollow drilling, compressed air drilling and for good bond conditions

 $f_{bd,PIR} = k_b \cdot f_{bd}$ 

fbd: Design value of the bond strength in N/mm² considering the concrete strength classes and the rebar diameter according to EN 1992-1-1: 2004+AC:2010 (for all other bond conditions multiply the values by 0,7)

k<sub>b</sub>: Bond efficiency factor according to table C1.2

Hammer drilling, hollow drilling and compressed air drilling											
bond strength f <sub>bd,PIR</sub> [N/mm²]											
Rebar / rebar	Concrete strength class										
anchor FRA	C12/15	C16/20	C20/25	C25/30	C30/37	C35/45	C40/50	C45/55	C50/60		
φ [mm]											
8 to 28	1,6	2,0	2,3	2,7	3,0	3,4	3,7	4,0	4,3		

Rebar connection with fischer injection mortar FIS V	
Performance	Annex C 1
Amplification factor $\alpha_{lb}$ , bond efficiency factor $k_b$ , design values of the bond strength $f_{bd,PlR}$	Appendix 19/ 21

# **Table C2.1:** Essential characteristics of **tensile resistance** for **fischer rebar anchors FRA** under fire exposure

concrete strength classes C12/C15 to C50/60, according to EN 1992-4

fischer rebar anchor FRA				M12	M16	M20	M24		
Stainless steel (FRA or FRA C)									
	R30	_	[N/mm²]	30					
Characteristic tensile resistance	R60			25					
	R90	σ <sub>Rk,s,fi</sub>		20					
	R120			16					

# Design value of the steel bearing capacity $\sigma_{\text{Rd},s,\text{fi}}$ under fire exposure for fischer rebar anchor FRA

The design value of the steel bearing capacity  $\sigma_{\text{Rd,s,fi}}$  under fire exposure has to be calculated by the following equation:

 $\sigma_{Rd,s,fi} = \sigma_{Rk,s,fi} / \gamma_{M,fi}$ 

with:

 $\sigma_{Rk,s,fi}$  Characteristic tensile resistance according to table C2.1  $\gamma_{M,fi}$  Partial factor according to EN 1992-1-2:2004+AC:2008

Rebar connection	with	fischer	injection	mortar	FIS	٧
------------------	------	---------	-----------	--------	-----	---

Design value of the steel bearing capacity  $\sigma_{\text{Rd,s,fi}}$  under fire exposure for fischer rebar anchor FRA

Annex C 2

Appendix 20/21

# Design values of the bond strength f<sub>bk,fi</sub> under fire exposure for concrete strength classes C12/15 to C50/60 (all drilling methods)

The design value of the bond strength f<sub>bk,fi</sub> under fire exposure has to be calculated by the following equation:

$$f_{bk,fi} = k_{fi}(\theta) \cdot f_{bd,PIR} \cdot \frac{\gamma_c}{\gamma_{M,fi}}$$

If: 
$$\theta > 74$$
 °C 
$$k_{fi}(\theta) = \frac{24,308 \cdot e^{-0,012 \cdot \theta}}{f_{bd,PIR} \cdot 4,3} \leq 1.0$$

If: 
$$\theta > \theta_{\text{max}}$$
 (317 °C)  $k_{\text{fi}}$  ( $\theta$ ) = 0

 $f_{bk,fi}$  = Design value of the bond strength in case of fire (in N/mm<sup>2</sup>)


(θ) = Temperature in °C in the mortar layer  $k_{fi}$  (θ) = Reduction factor under fire exposure

f<sub>bd,PIR</sub> = Design value of the bond strength in N/mm<sup>2</sup> in cold condition according to table C1.3 considering the concrete classes, the rebar diameter, the drilling method and the bond conditions according to EN 1992-1-1:2004+AC:2010

 $\gamma_{C}$  = Partial factor according to EN 1992-1-1:2004+AC:2010  $\gamma_{M,fi}$  = Partial factor according to EN 1992-1-2:2004+AC:2008

For evidence under fire exposure the anchorage length shall be calculated according to EN 1992-1-1:2004+AC:2010 Equation 8.3 using the temperature-dependent ultimate bond strength f<sub>bk,fi</sub>.

**Figure C3.1:** Example graph of reduction factor  $k_{fi}$  ( $\theta$ ) for concrete class C20/25 for good bond conditions



Rebar connection with fischer injection mortar FIS V

#### **Performance**

Design values of bond strength fbk,fi under fire exposure

Annex C 3

Appendix 21/21